

CLAIMS

1. A stent comprising a discontinuous expandable wall and a continuous covering layer of elastic material surrounding the discontinuous wall wherein the
5 continuous covering layer of elastic material is adhered to the discontinuous wall so it is intimately united with said discontinuous wall.

2. A stent according to claim 1, wherein the continuous covering layer of elastic material extends
10 at least partly radially within the discontinuous wall of the stent.

3. A stent according to claim 2, wherein the continuous covering layer of elastic material extends around and inside the discontinuous wall of the stent.

15 4. A stent according to claim 1, wherein the continuous covering layer is adhered to the discontinuous wall by means of a binder.

5. A stent according to claim 1, wherein the continuous covering layer is heat adhered to the
20 discontinuous wall.

6. A stent according to claim 1, wherein the continuous covering layer is chemically bonded to the discontinuous wall.

7. A stent according to claim 1, wherein the
25 continuous covering layer is adhered to the discontinuous wall by radial pressure of the discontinuous wall against the continuous covering layer.

8. A stent according to claim 1, wherein the
30 continuous covering layer has a structured surface towards the discontinuous wall, and wherein the continuous covering layer is adhered to the discontinuous wall as a result of said structured surface.

9. A method for applying a covering layer to a stent comprising:

radially contracting the stent;

inserting at least a portion of the
5 contracted stent into a tube the inner surface of which
has been previously done over with a lifting medium;

allowing the stent to radially expand in the
tube;

10 wetting the assembly tube plus stent with an
elastomeric polymerisable composition dissolved in a
sufficient amount of solvent to permit wet forming;

evaporating the solvent;

polymerizing the elastomeric composition in
the tube; and

15 taking the layer covered portion of the stent
out of the tube.

10. A method according to claim 9, wherein the
tube the inner surface of which has been done over with
a lifting medium is first wetted alone with the
20 elastomeric composition added with solvent, and wherein
the solvent is evaporated before the step of insertion
of the stent into the tube.

11. A method for applying a covering layer to a
stent comprising:

25 doing over a roll on surface with a lifting
medium;

coating said roll on surface with an
elastomeric polymerisable composition dissolved in a
sufficient amount of solvent to permit contact forming;

30 rolling at least a portion of the stent in
expanded condition on said coated roll on surface;

withdrawing the stent from the roll on
surface;

evaporating the solvent; and

Sub
B1

polymerizing the elastomeric composition adhered by contact on said portion of the stent.

12. A method for applying a covering layer to a stent comprising:

- 5 forming a tube of predetermined length with
an elastomeric polymerisable composition;
 radially contracting the stent;
 inserting into the tube a portion of the
stent corresponding to said predetermined length of the
10 tube; and
 allowing the stent to radially expand in the
tube, and welding the surfaces of contact between the
stent and the tube.

13. A method for applying a covering layer to a
15 stent comprising:

- forming a tube of predetermined length with
an elastomeric polymerisable composition;
 coating the inside of the tube with an
adhesive medium;
20 radially contracting the stent;
 inserting into the tube a portion of the
stent corresponding to said predetermined length of the
tube;
 allowing the stent to radially expand in the
25 tube; and
 allowing the adhesive medium to cure.

14. A method for applying a covering layer to a stent comprising:

- forming a tube of predetermined length with
30 an elastomeric polymerisable composition;
 coating the inside of the tube with an
elastomeric polymerisable composition dissolved in a
sufficient amount of solvent to permit contact forming;
 radially contracting the stent;

Sal
B1

inserting into the tube a portion of the
stent corresponding to said predetermined length of the
tube;

5 allowing the stent to radially expand in the
tube;

evaporating the solvent; and
polymerizing the elastomeric composition
adhered by contact to the tube and to the stent.

Sub
B1

ADD
B2